



TITLE:

RG59 Coaxial Cable

CODE:

SFX/59-PVC-WHT-100



DESCRIPTION:

100m RG59 Coaxial CCA White PVC

SUPPLIED AS:

Reel of 100m

- Even with the introduction of IP cameras, coax is still a preferred choice for many installers in the security industry
- Coax is a simple solution that does not require any additional products such as baluns to create an image
- Polyvinyl chloride plastic has excellent aging properties and will usually exceed a 25-30 year service life
- Suitable for general purpose CCTV applications and high frequency signal transmission
- Improved performance and protection against fire





Product Specification



Cable Construction

CPR	Eca
Conductor Diameter (mm)	0.58 ±0.008
Inner Conductor	Copper Clad Steel
Overall Diameter (mm)	6.10 ±0.10
Compliance and Standards	CE2014/30/EU, RoHS2 2011/65/EU, LVD 2014/35/EU

Insulation

Insulation	Solid PE
Insulation Colour	Clear
Insulation Thickness (mm)	1.60 ±0.01

Outer/Jacket Specification

Jacket	PVC
Overall Colour	White
Overall Diameter (mm)	6.10 ±0.10
Jacket Colour	White RAL 9003
Jacket Thickness (mm)	0.85 ±0.10

Electrical Characteristics

Outer Conductor DC resistance @ 20°C	<48Ω/km
Rated Temperature (°C)	-20°C to 80°C
Impedance	75Ω ±3Ω
Capacitance	>67nF/km



enquiries@securiflex.co.uk | www.securiflex.co.uk | 03333 44 66 23



MORE INFORMATION:

EURO CLASS (ca: cable)	CLASSIFICATION CRITERIA		CPR GUIDE		
	FIRE RATING	SFX COMMENT	Securi-Flex®		
Reaction to Fire BS EN ISO 1716			SUBCLASSIFICATIONS FOR EUROCLASSES B _{ca} to D _{ca}		
A_{ca}	Does not contribute to the fire	Due to availability, it will be almost impossible for a cable to meet A _{ca} , so they should only be specified with extreme caution.	(S) SMOKE PRODUCTION	(D) FLAMING DROPLETS	(A) SMOKE ACIDITY
Reaction to Fire BS EN 50399			BS EN 50399/BS EN 61034-2	BS EN 50399	BS EN 60754-2
B1_{ca}	Minimum contribution to the fire	It's highly unlikely the commonly-used cables will be classified to Class B1 _{ca} .	s1a: s1 + transmittance >=80% (BS EN 61034-2)	d0: No fall of droplets or flaming particles, times for 1200 seconds	a1: Very low acidity (conductivity <2.5 μS/mm & pH >4.3)
B2_{ca}	Combustible, low flame spread & heat release contribution to the fire	Similar to Class C _{ca} , although a lower acceptable heat release rate and burn measurement. In practice, this is likely to be the highest class cables will meet.	s1b: s1 + transmittance >=60% <80% (BS EN 61034-2)	d1: Fall of droplets or flaming particles that persist for less than 10 seconds, timed for 1200 seconds	a2: low acidity (conductivity <10 μS/mm & pH >4.3)
C_{ca}	Combustible, moderate flame spread & heat release	This is a more rigorous test than Class D _{ca} , this is widely accepted across Europe as the 'go to' classification, but be aware, many cables do not meet Class C _{ca} though availability is improving.	s1: Low production of slow propagation of smoke		
D_{ca}	Combustible, moderate flame spread & heat release	This classification has relatively little use or acceptance within specifying/contracting organisations. This is because no large scale fire growth is measured.	s2: Intermediate production & propagation of smoke	d2: None of the above	d2: None of the above
Reaction to Fire BS EN 60332-1-2			Visit us online: www.securiflex.co.uk The Trusted Cable Brand		
E_{ca}	Combustible, limited fire spread of less than 425mm	A basic test for vertical flame propagation for a single insulated wire or cable using a 1 KW pre-mixed flame. Note: This test does not measure heat release, toxic fumes or smoke.	Classes A to E have to be tested by an independent authorised laboratory. Most cables will fall into classes B2 _{ca} to E _{ca} . For a cable to meet A _{ca} , B1 _{ca} , B2 _{ca} or C _{ca} , there also needs to be regular on-going factory audits.		
F_{ca}	Combustible, fire spread of more than 425mm	Cables classified to Class F _{ca} may have high levels of flammability due to the materials they are made of. This does not mean that the cable cannot be used, it is more likely to be used external.			

OUR OPERATING TEMPERATURE RANGE GUIDE



Securi-Flex®

enquiries@securiflex.co.uk | www.securiflex.co.uk | 03333 44 66 23