

BELDEN QUIVALENTS



TITLE:

OSC Overall Foil Screened PE

CODE:

SFX/OSC10-PE-BLK-1000


DESCRIPTION:

1000m OSC10 10 Core 24AWG Overall Foil Screen 600V Black PE (9540)

SUPPLIED AS:

Reel of 1000m

- · Additional screening makes this cable suitable to be installed in areas where protection from electrical interferance is required
- Used for RS232 protocol
- Polyethylene plastic is excellent for use externally above ground or below ground inside ducting
- A quality alternative to genuine Belden cable
- **UV** resistant
- Can be cut to any length required saving instillation time



































Product Specification



Cable Construction

Cable Construction	10 Cores
CPR	Fca
Conductor	Tinned Copper
Conductor Diameter (mm)	0.19 ±0.008 x 7(0.22mm²)
Stranded Diameter (mm)	0.22
Overall Diameter (mm)	6.20 ±0.20

Insulation

Insulation	PVC
Insulation Colour	Red,Black,White,Green,Blue,Brown,Orange,Yellow,Violet,Grey
Insulation Resistance @20°C	>200MO/km
Insulation Thickness (mm)	0.3

Outer/Jacket Specification

Jacket	PE
Overall Colour	Black
Overall Diameter (mm)	6.20 ±0.20
Jacket Colour	Black RAL 9005
Jacket Thickness (mm)	0.50

Electrical Characteristics

Insulation Resistance @20°C	>200MO/km
Max Conductor DC resistance @ 20°C	<90.00O/km
Rated Temperature (°C)	-20°C to 80°C
Rated Voltage (V)	600V























BELDEN EQUIVALENTS



MORE INFORMATION:

EURO	CLASSIFICATION CRITERIA				
CLASS (ca:cable)	FIRE RATING	SFX COMMENT	CPR GUII	DE <i>Sec</i>	curi-Flex®
Reaction to Fir	e BS EN ISO 1716		SUBCLASSIFICATIONS FOR EUROCLASSES Bca to Dca		
A _{ca}	Does not contribute to the fire	Due to availability, it will be almost impossible for a cable to meet Aca, so they should only be specified with extreme caution.	(S) SMOKE PRODUCTION	(D) FLAMING DROPLETS	(A) SMOKE ACIDITY
Reaction to Fir	e BS EN 50399		BS EN 50399/BS EN 61034-2	BS EN 50399	BS EN 60754-2
B1 _{ca}	Minimum contribution to the fire	It's highly unlikely the commonly-used cables will be classified to Class B1ca.	s1a: s1 + transmittance >=80% (BS EN 61034-2)	d0: No fall of droplets or flaming particles, times for 1200 seconds	a1: Very low acidity (conductivity <2.5 µS/mm & pH >4.3)
B2 _{ca}	Combustible, low flame spread & heat release contribution to the fire	Similar to Class Cca, although a lower acceptable heat release rate and burn measurement. In practice, this is likely to be the highest class cables will meet.	s1b: s1 + transmittance >=60% <80% (BS EN 61034-2)	d1: Fall of droplets or	a2: low acidity
Cca	Combustible, moderate flame spread & heat release	This is a more rigorous test than Class Dca, this is widely accepted across Europe as the 'go to' classification, but be aware, many cables do not meet Class Cca though availability is improving.	s1: Low production of slow propagation of smoke s2: Intermediate	flaming particles that persist for less than 10 seconds, timed for 1200 seconds	(conductivity <10 μS/mm & pH >4.3)
D _{ca}	Combustible, moderate flame spread & heat release	This classification has relatively little use or acceptance within specifying/contracting organisations. This is because no large scale fire growth is measured.	production & propagation of smoke s3: None of the above	d2: None of the above	d2: None of the above
Reaction to Fir	e BS EN 60332-1-2				
E _{ca}	Combustible, limited fire spread of less than 425mm	A basic test for vertical flame propagation for a single insulated wire or cable using a 1 kW pre-mixed flame. Note: This test does not measure heat release, toxic fumes or smoke.	Visit us onlin www.securiflex		The Trusted Cable Brand
F _{ca}	Combustible, fire spread of more than 425mm	Cables classified to Class Fca may have high levels of flammability due to the materials they are made of. This does not mean that the cable cannot be used, it is more likely to be used external.	Classes A to E have to be tester Most cables will fall into classes For a cable to meet Aca, B1ca, factory audits.	B2ca to Eca.	*

OUR OPERATING TEMPERATURE RANGE GUIDE











enquiries@securiflex.co.uk | www.securiflex.co.uk | 03333 44 66 23









