

**TITLE:**

Telecom Budget CCS PVC

CODE:

SFX/TC-4-PVC-WHT-100



DESCRIPTION:

100m Budget 4pr CCS Telecom Cable
White PVC

SUPPLIED AS:

Reel of 100m

- A budget telecoms cable
- Suitable for security alarm and low voltage applications
- Polyvinyl chloride plastic has excellent aging properties and will usually exceed a 25-30 year service life
- Colour coded insulation
- Easy to install light weight cable





Product Specification

25-YEAR WARRANTY

Cable Construction

Cable Construction	4 Pairs
CPR	Fca
Conductor	Copper Clad Steel
Conductor Diameter (mm)	0.50 ±0.02
Overall Diameter (mm)	4.60 ±0.20

Insulation

Insulation	PVC
Insulation Colour	White/Blue, Blue/White, White/Orange, Orange/White, White/Green, Green/White, White/Brown, Brown/White
Insulation Resistance @20°C	>200MO/km
Insulation Thickness (mm)	0.185

Outer/Jacket Specification

Jacket	PVC
Overall Colour	White
Overall Diameter (mm)	4.60 ±0.20
Jacket Colour	White RAL 9003
Jacket Thickness (mm)	0.45
Nylon Rip-Cord	210D

Electrical Characteristics

Insulation Resistance @20°C	>200MO/km
Max Conductor DC resistance @ 20°C	<501.90/km
Rated Temperature (°C)	-20°C to 80°C
Rated Voltage (V)	30V

**enquiries@securiflex.co.uk | www.securiflex.co.uk | 03333 44 66 23**



MORE INFORMATION:

EURO CLASS (ca: cable)	CLASSIFICATION CRITERIA		CPR GUIDE	
	FIRE RATING	SFX COMMENT		Securi-Flex®
Reaction to Fire BS EN ISO 1716			SUBCLASSIFICATIONS FOR EUROCLASSES B _{ca} to D _{ca}	
A_{ca}	Does not contribute to the fire	Due to availability, it will be almost impossible for a cable to meet A _{ca} , so they should only be specified with extreme caution.	(S) SMOKE PRODUCTION	(D) FLAMING DROPLETS
Reaction to Fire BS EN 50399			BS EN 50399/BS EN 61034-2	BS EN 50399
B1_{ca}	Minimum contribution to the fire	It's highly unlikely the commonly-used cables will be classified to Class B1 _{ca} .	s1a: s1 + transmittance ≥80% (BS EN 61034-2)	d0: No fall of droplets or flaming particles, times for 1200 seconds
B2_{ca}	Combustible, low flame spread & heat release contribution to the fire	Similar to Class C _{ca} , although a lower acceptable heat release rate and burn measurement. In practice, this is likely to be the highest class cables will meet.	s1b: s1 + transmittance ≥60% <80% (BS EN 61034-2)	d1: Fall of droplets or flaming particles that persist for less than 10 seconds, timed for 1200 seconds
C_{ca}	Combustible, moderate flame spread & heat release	This is a more rigorous test than Class D _{ca} , this is widely accepted across Europe as the 'go to' classification, but be aware, many cables do not meet Class C _{ca} though availability is improving.	s1: Low production of slow propagation of smoke	a1: Very low acidity (conductivity <2.5 μS/mm & pH >4.3)
D_{ca}	Combustible, moderate flame spread & heat release	This classification has relatively little use or acceptance within specifying/contracting organisations. This is because no large scale fire growth is measured.	s2: Intermediate production & propagation of smoke	a2: low acidity (conductivity <10 μS/mm & pH >4.3)
Reaction to Fire BS EN 60332-1-2			s3: None of the above	d2: None of the above
E_{ca}	Combustible, limited fire spread of less than 425mm	A basic test for vertical flame propagation for a single insulated wire or cable using a 1 KW pre-mixed flame. Note: This test does not measure heat release, toxic fumes or smoke.	Visit us online: www.securiflex.co.uk	
F_{ca}	Combustible, fire spread of more than 425mm	Cables classified to Class F _{ca} may have high levels of flammability due to the materials they are made of. This does not mean that the cable cannot be used, it is more likely to be used external.	The Trusted Cable Brand	

OUR OPERATING TEMPERATURE RANGE GUIDE



Securi-Flex®

enquiries@securiflex.co.uk | www.securiflex.co.uk | 03333 44 66 23